



E-glass spray up roving

CAS Number	65997-17-3
Alkali content (R2O)	≤ 0.8%
Filament diameter	13 μm
Loss of Ignitions	1.25%± 25%
Moisture content	≤ 0.20%
Compatible resins	Polyester
Coupling agent	Silane
Bending strenght	289 MPa
Bending modulus	9.8 MPa
Resin content	56.1%