



Modified Sodium Disilicate

Appearance	Free flowing powder or granular
CA+ exchange (mgCaCO ₃ /g), 35 iae	A: 450 min B: 420 min C: 380 min
Na ₂ O + SiO ₂ by wt %	A: 60 min B: 50 min C: 45 min
Whiteness %	90 min
Bulk density (g/l) – Powder	0.60 - 0.80
Bulk density (g/l) – Granular	0.38 – 0.55
pH of 1% water solution	12.5 max
Moisture by wt %	4.0 max
Water insoluble by wt %	1.5 max